

Cite this as: Hong-xiang Ou, Chen-xia Gong, Hong-lai Xue, Dong-sheng Zhou, Kai-jia Li, Shu-cheng Liu, 2021. Adsorption of tetrodotoxin by flexible shape-memory polymers synthesized from silica-stabilized Pickering high internal phase emulsion. *Journal of Zhejiang University-SCIENCE A (Applied Physics & Engineering)*, 22(10):805-818. <https://doi.org/10.1631/jzus.A2000433>

Adsorption of tetrodotoxin by flexible shape-memory polymers synthesized from silica-stabilized Pickering high internal phase emulsion

Key words:

Tetrodotoxin; SiO₂; Imidazolium-modified bromobutyl rubber; Pickering HIPEs; Adsorption

Innovation

- SiO₂ nanoparticles were used as stable particles of the emulsion and joined together by Pickering HIPES polymerization, which made it convenient to collect the adsorbent after adsorption.
- The highly viscoelastic imidazolium-modified bromobutyl rubber (IBR) was uniformly distributed on the gap and surface of the polymers, which resulted in polymers with good mechanical properties and shape-memory function.

Methodology





Fig. 1 Formation of $\text{SiO}_2@IBR$ with macroporous structure and good flexibility derived from Pickering O/W HIEPs

Characterizations: Viscoelasticity and morphology




Fig. 2 Viscoelasticity and mechanical properties test




Fig. 3 SEM Images of SiO₂@IBR

Characterizations: Shape memory property



Fig. 4 Compression testing of $\text{SiO}_2@IBR$

Adsorption Performance




Fig. 5 Kinetic data and modeling for adsorption of TTX onto SiO₂@IBR (a) and Intra-particle diffusion modeling for adsorption of TTX onto SiO₂@IBR (b)

Adsorption Performance




Fig. 6 Equilibrium data and modeling for adsorption of TTX onto $\text{SiO}_2@IBR$ (a) and Regeneration of $\text{SiO}_2@IBR$ for ten cycles (b)

Conclusions

- The SiO₂@IBR polymers have well-defined macroporous structure and good flexibility. The particular shape memory of SiO₂@IBR is beneficial to the adsorption and regeneration process.
- SiO₂@IBR is an effective and promising adsorbent with good adsorption capacity for TTX. The results of the pseudo-first-order and pseudo-second-order kinetic models indicated that there was chemical bonding accompanied by physical adsorption.
- The regeneration experiments results demonstrated that SiO₂@IBR has good adsorption regeneration performance. After 10 regeneration experiments, the adsorption capacity decreased less than 0.03%.

